

PRODUCT DATA SHEET

SikaGrout[®]-800

High performance more sustainable cementitious grout

DESCRIPTION

SikaGrout[®]-800 is a cementitious, high performance, shrinkage compensated engineering grout. It contains recycled materials and can reduce the carbon footprint when compared to a reference cementitious grout in a Life Cycle Assessment.

USES

The Product is used for:

- Grouting heavy equipment or machine bases
- Grouting under support base plates
- Bedding joints in precast concrete sections
- Sealing around penetrations
- Steel reinforcement anchoring
- Repairing concrete structures and components
- Interior or exterior applications

Please note:

- The Product may only be used by experienced professionals.

CHARACTERISTICS / ADVANTAGES

- Uses recycled raw materials
- Application thickness 6 mm to 300 mm
- Dust reduced
- Sulphate resistant
- High final strengths
- Shrinkage compensated both in plastic and hardening stage
- Fluid consistency
- No segregation or bleeding
- Ready to use, just add water
- Easy to mix and apply
- Can be pumped or poured
- Low permeability
- Non-corrosive

SUSTAINABILITY

- Contributes towards satisfying Materials and Resources (MR) Credit: Building product disclosure and optimization — Environmental Product Declarations under LEED[®] v4
- Contributes towards satisfying Materials and Resources (MR) Credit: Building Product Disclosure and Optimization — Sourcing of Raw Materials under LEED[®] v4
- Contributes towards satisfying Materials and Resources (MR) Credit: Building Product Disclosure and Optimization — Material Ingredients under LEED[®] v4

APPROVALS / CERTIFICATES

- CE marking and declaration of performance based on EN 1504-3:2005 Products and systems for the protection and repair of concrete structures — Structural and non-structural repair
- CE marking and declaration of performance based on EN 1504-6:2004 Products and systems for the protection and repair of concrete structures — Anchoring reinforcing steel bar

PRODUCT DATA SHEET

SikaGrout[®]-800

January 2023, Version 01.01
020201010010000459

THIS DOCUMENT SERVES ONLY AS AN ILLUSTRATION OF A SIKA PRODUCT DURING THE SALES PROCESS AND THEREFORE, IS NOT BINDING FOR LOCAL SALE. PLEASE CONSULT THE LOCAL COUNTRY PRODUCT DATA SHEET FOR SPECIFIC TERMS AND CONDITIONS.

PRODUCT INFORMATION

Composition	Sulphate resistant and replacement cement, selected aggregates and additives	
Packaging	Standard bag	25 kg
	Refer to the current price list for available packaging variations.	
Shelf life	Standard bag	12 months from date of production
Storage conditions	The Product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +35 °C. Always refer to the packaging Refer to the current Safety Data Sheet for information on safe handling and storage.	
Appearance and colour	Grey powder	
Maximum grain size	2 mm	
Soluble chloride ion content	≤ 0.05 %	(EN 1015-17)

TECHNICAL INFORMATION

Compressive strength	Cured 24 h at 21 °C	30 MPa	(EN 12190)
	Cured 7 d at 21 °C	55 MPa	
	Cured 28 d at 21 °C	80 MPa	
Modulus of elasticity in compression	Cured 28 d at 21 °C	32 GPa	(EN 13412)
Tensile strength in flexure	Conditioned 24 h at 20 °C	6 MPa	(EN 12190)
	Conditioned 7 d at 20 °C	8 MPa	
	Conditioned 28 d at 20 °C	10 MPa	
Tensile adhesion strength	≥ 2.0 MPa		(EN 1542)
Pull-out resistance	≤ 0.6 mm at load of 75 kN		(EN 1881)
Shrinkage	Linear: ≤ 0.7 mm/m after 91 days		(EN 12617-4)
Restrained shrinkage / expansion	≥ 2.0 MPa		(EN 12617-4)
Thermal compatibility	≥ 2.0 MPa (Part 1 - Freeze-Thaw)		(EN 1770)
Carbonation resistance	dk ≤ control concrete MC (0.45)		(EN 13295)
Reaction to fire	Class A1		(EN 1504-3)

APPLICATION INFORMATION

Mixing ratio	Fluid consistency	3.10 L to 3.25 L
	Fluid consistency — water ratio by weight	12.4 % to 13 %
Fresh mortar density	2.25 kg/l	
Consumption	2.3 kg/m ² per mm thickness Note: Consumption data is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.	

Yield	12.7 L of mortar per 25 kg bag	
Layer thickness	Maximum	300 mm
	Minimum	6 mm
Material temperature	Maximum	+35 °C
	Minimum	+5 °C
Ambient air temperature	Maximum	+35 °C
	Minimum	+5 °C
Substrate temperature	Maximum	+35 °C
	Minimum	+5 °C
Pot Life	At 20 °C	45 minutes
<p>Pot life depends on temperature Note: Pot life will be shorter at higher temperatures. Pot life will be longer at lower temperatures.</p>		

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

CONCRETE

Prepare the concrete to provide a mechanical key and to remove any contamination which will impair the grout flow or reduce adhesion strength.

1. Remove laitance, delaminated, weak, damaged and deteriorated concrete using appropriate preparation equipment.
2. Clean any pockets or holes for structural fixings from all debris and water.

The substrate is structurally sound and thoroughly clean with a textured finish exposing the aggregate.

STEEL

Prepare the steel to remove any contamination which will impair the grout flow or reduce adhesion strength.

1. Clean the substrate using grinding, abrading or shot blasting equipment.

The substrate is thoroughly clean and free from oil, grease, rust and scale.

SHUTTERING OR FORMWORK

Where formwork is to be used, all formwork must be adequate strength, treated with release agent and sealed to prevent leakage of pre-wetting water and grout.

1. If vacuum extraction equipment is not used to remove pre-soak water ensure the formwork includes outlets for the pre-soaked water to drain.
2. For manual grout application, construct a header box or hopper on one side of the formwork so that a minimum grout head of 150-200 mm can be maintained during the grouting operation.

MIXING

ELECTRIC SINGLE OR DOUBLE PADDLE MIXER IMPORTANT

Do not add more water than the maximum specified

1. Pour the minimum amount of water into a suitable clean mixing container.
2. Stir the water slowly with a spiral paddle (300 to 500 rpm).
3. Add the complete bag of powder into the water.
4. Mix continuously for 3 minutes to achieve a uniform and lump free smooth consistency.
5. Add more water within the mixing time up to the maximum allowed until the required consistency is achieved.
6. Wait for 2 to 3 minutes to release entrained air bubbles.
7. Mix again for 1 more minute.

GROUT MIXER IMPORTANT

Carry out equipment trials

Carry out equipment trials to make sure the Product can be mixed satisfactory before full project application.

PRODUCT DATA SHEET

SikaGrout®-800

January 2023, Version 01.01

020201010010000459

IMPORTANT

Do not use continuous mixing equipment

The Product is not designed for processing with continuous mixing equipment.

1. Pour the minimum water ratio in the correct proportion into the grout mixer.
2. While stirring the water, slowly add the powder.
3. Add more water within the mixing time up to the maximum allowed until the required consistency is achieved.
4. Mix continuously for a minimum of 3 minutes. For larger mixes the mixing time must be extended to approximately 5 minutes or as necessary.
5. Mix until the grout achieves a lump free smooth consistency.

APPLICATION

IMPORTANT

Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

IMPORTANT

Application in the direct sun or strong winds

Avoid application in direct sun, strong winds or both to reduce the risk of the Product cracking.

PRE-SOAKING

1. Thoroughly saturate the prepared concrete substrate with clean water for 12 hours before application of the grout.
2. Do not allow the substrate to dry within this time.
3. Remove all water from within the formwork, cavities or pockets.

The final surface must achieve a dark matt appearance (saturated surface dry) without glistening.

PLACING MANUAL APPLICATION

After mixing, allow material to remain in the mixing container for ~3 minutes to release entrained air bubbles.

1. **IMPORTANT** Avoid trapping air. Pour the mixed grout into the header box or hopper ensuring continuous grout flow during the complete grouting operation.

PLACING GROUT PUMP APPLICATION

Use grout pumps for large volume placement.

1. Conduct equipment trials to confirm the product can be pumped satisfactory before full project application

SURFACE FINISHING

1. **IMPORTANT** Do not add water to the surface and do not overwork the surface during finishing. Finish exposed grout surfaces to the required surface texture as soon as the grout has started to stiffen.
2. Remove the formwork when the grout has initially hardened
3. Trim the grout edges while the concrete is "green"

Cold weather working

Note: Risk of reduced strength gain and physical properties

1. Store bags in a warm environment.
2. Use warm mixing water to assist with achieving strength gain and maintaining physical properties.

Hot weather working

Note: Increased risk of cracking and reduction of physical properties

1. Store bags in a cool environment.
2. Use cold mixing water to assist with controlling the exothermic reaction to reduce cracking and maintaining physical properties.

CURING TREATMENT

Protect exposed grout surfaces after finishing from premature drying and cracking using an appropriate curing method such as curing compounds, moist geotextile membranes, hessian or polythene sheeting. In cold weather, apply insulated blankets to maintain a constant temperature to prevent surface damage from freezing and frost.

PRODUCT DATA SHEET

SikaGrout®-800

January 2023, Version 01.01

020201010010000459

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Services AG

Tüffenwies 16
8048 Zürich
Tel: +41 58 436 4040
www.sika.com



PRODUCT DATA SHEET

SikaGrout®-800

January 2023, Version 01.01
020201010010000459

SikaGrout-800-en-CORP-(01-2023)-1-1.pdf